



TECHNICAL DATA SHEET

ALPI

ALPIlignum /

ALPIlignum is a decorative veneer made of reconstituted wood.

In line with the company's sustainable approach, ALPI veneer is made with wood from responsibly managed forests certified by the FSC® (FSC-Coo4666).



Standard dimensions /

Poplar based veneer	length 2200-2500 mm; width from 620 to 700 mm
Ayous based veneer	length 2200-2500-2800-3150 mm; width 360 mm, from 620 to 760 mm
Basswood based veneer	length 2500-3150 mm; width 360 mm, from 620 to 700 mm

Special sizes available on request.

Nominal thickness available /

Thickness	from 0,42 mm to 2,8 mm
-----------	------------------------

Not all products are available in all thicknesses.

Variations in size /

Width	-0 / +30 mm
Thickness	complies with standard ISO 18775 < 1,5 mm : +/- 0,05 mm; > 1,5 mm : +/- 4%

Wood Density /

450-900 kg/m³ (measured according to ISO 9427). Density depends on each product.

ALPIlignum /

Formaldehyde emissions /

Measured according to the standard UNI EN 717-1:2004, the formaldehyde emission of ALPIlignum complies with EU REACH Regulation Eo5 under EU 2023/1464. It is impossible to guarantee the absolute absence of formaldehyde, because traces of it are naturally present in wood.

Lightfastness /

ALPIlignum is an uncoated product whose lightfastness depends on the chemical composition of the final varnish and how it is applied. Upon request, ALPI supplies a type of ALPIlignum that can reach values above 4 in grey scale (UNI EN 15187:2024) if suitably varnished. Customers must be aware that exposure to light can make the veneer fade or change colour. ALPI suggests making precautionary tests based on the planned use in order to optimise performance.

Mechanical characteristics /

The mechanical characteristics of ALPIlignum depend on the chemical composition of the varnish used and the type of surface material the veneer is affixed to. ALPI suggests making precautionary tests based on the planned use in order to optimise performance.

Colour and grain /

Being a natural wood product, the colour of ALPIlignum may vary slightly from the reference colour. ALPI suggests verifying the colour and veining of the acquired veneer before use.

Storing /

Being prevalently made of wood, the humidity content of ALPIlignum varies in accordance with the humidity of the space where it is stored and processed. ALPI suggests maintaining relative humidity levels between 40% and 70%, with a reference ambient temperature of 20° Celsius.

Precautions /

Absolutely avoid contact, even temporary contact, with water and other liquids. Absolutely avoid condensation and dripping on the surface of the product. ALPIlignum must be stored flat, at least 20 centimetres from the ground, and protected from direct and indirect light.

ALPIlignum /

Veneering /

Gluing with urea adhesives

ALPIlignum can be glued with urea adhesive to all wood-based surfaces. Other types of surface must be tested and evaluated beforehand. The amount of glue per square metre depends on the material and thickness of the surface, on the structure and thickness of the veneer, and on press pressure. Generally, no more than 150 grams of glue per square metre is advised, combined with pressure between 1.5 and 5 bar. Veneering temperatures are between 85° and 120° Celsius. Glue may be mixed with organic or inorganic additives in order to modify the spread rate to reduce the effect of bleed-through, the occurrence of glue seeping through the pores of the wood and showing up on the face of the panel. Adding pigment to the glue in a colour similar to the veneer is advisable. ALPIlignum made of basswood must be glued with at least 120-140 grams of urea adhesive per square metre.

Gluing with vinyl adhesives

ALPIlignum veneer can be glued with vinyl adhesive to all wood-based surfaces. Other types of surface must be tested and evaluated beforehand. Being thermoplastic, this type of adhesive must be applied in a precise quantity according to the veneer, the type of surface it is affixed to, and the type of press in order to avoid bleed-through that is difficult to eliminate by sanding. In general, between 80 grams and 100 grams of glue per square metre should be used, with pressure between 1.5 and 3.5 bar. Veneering temperatures are between 60° and 90° Celsius. Adding pigment to the glue in a colour similar to the veneer is advisable. ALPI suggests making tests before use.

Gluing with hot-melt adhesives

ALPIlignum can be glued using hot-melt adhesives such as polyolefin, EVA (ethylene vinyl acetate), and reactive polyurethane. Hot-melt adhesive is mainly used on small surfaces such as edges, with the help of automatic systems with a mechanical clamp. Other methods of veneering must be verified by preliminary testing. ALPI recommends following the instructions of the adhesive manufacturer.

Sanding /

After gluing it to the desired surface, ALPIlignum must be sanded with abrasive paper to eliminate imperfections and glue that has seeped through the pores. Sandpaper with grit grades 120–150–180 can be used singularly or in sequence, by hand or by electric sander. Grit grades 100 or 220/240 should only be used to obtain special effects.

Varnishing /

Like all other wood, ALPIlignum requires specific varnish to protect and preserve it from chemical and physical deterioration given by light and heat, and from mechanical damage such as scratches and dents.

ALPIlignum can be varnished using all methods and types of product that are recommended for wood. Special attention is needed when using water-based varnish, seeing the hygroscopic nature of wood veneer.

ALPI suggests using products with high wetting capacity, yellowing resistance, and high protection from ultraviolet rays.

Any water-based varnish used must remain stable in moderately acid pH (4–6) conditions, such as products specifically formulated for acidic broad-leaved (hardwood) types of wood. ALPI recommends following the instructions of the varnish manufacturer and conducting preliminary tests before proceeding.

For all additional clarifications, please contact the technical support office at ALPI. This data sheet replaces and annuls any older information. The information and recommendations contained in this data sheet are based on current knowledge at ALPI and could be modified in the future in accordance with new findings, evaluations or production systems.

Users should carry out their own assessment of the product to satisfy themselves that it is suitable for their requirements.

ALPIlignum Radiant /

ALPIlignum Radiant is a veneer made of reconstituted wood with decorative pinstripes in clear polycarbonate.

In line with the company's sustainable approach, ALPI veneer is made with wood from responsibly managed forests certified by the FSC® (FSC-C004666).



Standard dimensions /

Poplar based veneer	length 2500 mm width 300 mm - 420 mm
Ayous based veneer	length 2500 mm width 300 mm - 420 mm
Basswood based veneer	length 2500 mm width 300 mm - 420 mm
Veneer nominal thickness	0.6 - 0.8 mm

ALPIlignum Radiant /

Formaldehyde emissions /

Measured according to the standard UNI EN 717-1:2004, the formaldehyde emission of ALPIlignum complies with EU REACH Regulation Eo5 under EU 2023/1464.

It is impossible to guarantee the absolute absence of formaldehyde, because traces of it are naturally present in wood.

Lightfastness /

ALPIlignum Radiant is an uncoated product whose lightfastness depends on the chemical composition of the final varnish and how it is applied. Upon request, ALPI supplies a type of ALPIlignum Radiant that can reach values above 4 in grey scale (UNI EN 15187:2024) if suitably varnished. Customers must be aware that exposure to light can make the veneer fade or change colour. ALPI suggests making precautionary tests based on the planned use in order to optimise performance.

Mechanical characteristics /

The mechanical characteristics of ALPIlignum Radiant depend on the chemical composition of the varnish used and the type of substrate the veneer is affixed to. ALPI suggests making precautionary tests based on the planned use in order to optimise performance.

Colour and grain /

Being a natural wood product, the colour of ALPIlignum Radiant may vary slightly from the reference colour. ALPI suggests verifying the colour and veining of the acquired veneer before use.

Storing /

Being prevalently made of wood, the humidity content of ALPIlignum Radiant varies in accordance with the humidity of the space where it is stored and processed. ALPI suggests maintaining relative humidity levels between 40% and 70%, with a reference ambient temperature of 20° Celsius.

Precautions /

Absolutely avoid contact, even temporary contact, with water and other liquids. Absolutely avoid condensation and dripping on the surface of the product. ALPIlignum Radiant must be stored flat, at least 20 centimetres from the ground, and protected from direct and indirect light.

ALPIlignum Radiant /

Backing /

ALPIlignum Radiant can be affixed to polymethyl methacrylate (PMMA), polycarbonate, copolyester (PETG), polyvinyl chloride (PVC), polyester (PET) and glass. Increased attention is due if the rear of the panel is visible. Using opaline, fumé, coloured or textured surfaces can help. The veneer can be affixed to other materials, which must be tested and evaluated beforehand.

Cutting /

ALPIlignum Radiant can be trimmed with a professional veneer guillotine with a single bevelled blade that cuts downward orthogonally to produce a clean cut. High-power laser cutting is another option for straight, crisp results. Alternatively, the veneer can be cut using a hand-held blade and a metal set square. When cutting lengthwise along the grain, ALPI recommends slicing down the centre of a wood section to obviate any deviation or divergence of the polycarbonate stripes.

Joining veneer sheets /

Edges can be spliced together manually with tape to form a wider piece. Tape is applied to the outward facing side, and removed after the veneering process. Alternatively, automatic seaming systems can be used.

Veneering /

ALPIlignum Radiant can be affixed to the above-mentioned plastics using polyurethane hot-melt adhesive. For optimal aesthetic results, once the veneer is affixed to the substrate, the panel is placed under a cold press to improve even spreading of the glue. Solvent-based acrylic glue or double-sided tape are recommended only if the rear of the panel will not be visible. When gluing to glass, the use of EVA (ethylene vinyl acetate) glue under vacuum press is advised. Other types of adhesive and other types of substrates must be tested before use.

Sanding /

ALPIlignum Radiant being a composite material made of wood and plastic, the sanding process must use the proper type of belt and the proper speed. This will avoid overheating the plastic stripes, causing them to become wavy, and prevent too much wood being worn away. ALPI recommends reducing the speed of the sanding belt by 20% to 30% compared to the standard sanding speed for all-wood veneer. Abrasive paper with grit size 150–180 is appropriate.

Varnishing /

ALPIlignum Radiant can be coated with two-component acrylic varnish, two-component polyurethane varnish, ultraviolet-cured acrylic varnish, and water-based varnish – all in various degrees of shine. ALPI recommends testing other types of varnish before proceeding.

Helpful tips /

To avoid alignment defects, it is possible in the joining phase to insert a section of ALPIlignum between two sections of ALPIlignum Radiant. This makes misalignment of the parallel stripes less visible. When installing the panels of ALPIlignum Radiant, it is possible to use profiles of wood, aluminium or other materials as connectors between the panels for pleasing aesthetic results. Heat generated by back-lighting could cause panels of ALPIlignum Radiant to warp. Light-emitting diodes are recommended, as is ventilation that allows heat to dissipate.

For all additional clarifications, please contact the technical support office at ALPI. This data sheet replaces and annuls any older information. The information and recommendations contained in this data sheet is based on current knowledge at ALPI and could be modified in the future in accordance with new findings, evaluations or production systems. Users should carry out their own assessment of the product to satisfy themselves that it is suitable for their requirements.

ALPIlignum Sushi /

ALPIlignum Sushi is a decorative veneer made of reconstituted wood with metallic effect powders.

In line with the company's sustainable approach, ALPI veneer is made with wood from responsibly managed forests certified by the FSC® (FSC-C004666).



Standard dimensions /

Poplar based veneer

length 2200 mm width 620 mm

ALPIlignum Sushi /

Formaldehyde emissions /

ALPIlignum Sushi is devoid of added formaldehyde. However, it is impossible to guarantee the absolute absence of formaldehyde, because traces of it are naturally present in wood.

Lightfastness /

ALPIlignum Sushi is an uncoated product whose lightfastness depends on the chemical composition of the final varnish and how it is applied. Upon request, ALPI supplies a type of ALPIlignum Sushi that can reach values above 4 in grey scale (UNI EN 15187:2024) if suitably varnished. Customers must be aware that exposure to light can make the veneer fade or change colour. ALPI suggests making precautionary tests based on the planned use in order to optimise performance.

Mechanical characteristics /

The mechanical characteristics of ALPIlignum Sushi depend on the chemical composition of the varnish used and the type of surface material the veneer is affixed to. ALPI suggests making precautionary tests based on the planned use in order to optimise performance.

Colour and grain /

Being a natural wood product, the colour of ALPIlignum Sushi may vary slightly from the reference colour. ALPI suggests verifying the colour and veining of the acquired veneer before use. The veining pattern varies from sheet to sheet.

Storing /

Being prevalently made of wood, the humidity content of ALPIlignum Sushi varies in accordance with the humidity of the space where it is stored and processed. ALPI suggests maintaining relative humidity levels between 40% and 70%, with a reference ambient temperature of 20° Celsius.

Precautions /

Absolutely avoid contact, even temporary contact, with water and other liquids. Absolutely avoid condensation and dripping on the surface of the product. ALPIlignum Sushi must be stored flat, at least 20 centimetres from the ground, and protected from direct and indirect light.

ALPIlignum Sushi /

Veneering /

Gluing with urea adhesives

ALPIlignum Sushi can be glued with urea adhesive to all wood-based surfaces. Other types of surface must be tested and evaluated beforehand. The amount of glue per square metre depends on the material and thickness of the surface, on the structure and thickness of the veneer, and on press pressure. Generally, no more than 150 grams of glue per square metre is advised, combined with pressure between 1.5 and 5 bar. Veneering temperatures are between 85° and 120° Celsius. Glue may be mixed with organic or inorganic additives in order to modify the spread rate to reduce the effect of bleed-through, the occurrence of glue seeping through the pores of the wood and showing up on the face of the panel. Adding pigment to the glue in a colour similar to the veneer is advisable.

Gluing with vinyl adhesives

ALPIlignum Sushi can be glued with vinyl adhesive to all wood-based surfaces. Other types of surface must be tested and evaluated beforehand. Being thermoplastic, this type of adhesive must be applied in a precise quantity according to the veneer, the type of surface it is affixed to, and the type of press in order to avoid bleed-through that is difficult to eliminate by sanding. In general, between 80 grams and 100 grams of glue per square metre should be used, with pressure between 1.5 and 3.5 bar. Veneering temperatures are between 60° and 90° Celsius. Adding pigment to the glue in a colour similar to the veneer is advisable. ALPI suggests making tests before use.

Gluing with hot-melt adhesives

ALPIlignum Sushi can be glued using hot-melt adhesives such as polyolefin, EVA (ethylene vinyl acetate), and reactive polyurethane. Hot-melt adhesive is mainly used on small surfaces such as edges, with the help of automatic systems with a mechanical clamp. Other methods of veneering must be verified by preliminary testing. ALPI recommends following the instructions of the adhesive manufacturer.

Sanding /

After gluing it to the desired surface, ALPIlignum Sushi must be sanded with abrasive paper to eliminate imperfections and glue that has seeped through the pores. Sandpaper with grit grades 120–150–180 can be used singularly or in sequence, by hand or by electric sander. Grit grades 100 or 220/240 should only be used to obtain special effects.

Varnishing /

Like all other wood, ALPIlignum Sushi requires specific varnish to protect and preserve it from chemical and physical deterioration given by light and heat, and from mechanical damage such as scratches and dents.

ALPIlignum Sushi can be varnished using all methods and types of product that are recommended for wood. Best results are obtained by first applying a two-component water-based primer, 70–90 grams per square metre, after which other layers of varnish can be applied. ALPI suggests using products with high wetting capacity, yellowing resistance, and high protection from ultraviolet rays.

Any water-based varnish used must remain stable in moderately acid pH (4–6) conditions, such as products specifically formulated for acidic broad-leaved (hardwood) types of wood. ALPI recommends following the instructions of the varnish manufacturer and conducting preliminary tests before proceeding.

For all additional clarifications, please contact the technical support office at ALPI. This data sheet replaces and annuls any older information. The information and recommendations contained in this data sheet are based on current knowledge at ALPI and could be modified in the future in accordance with new findings, evaluations or production systems.

Users should carry out their own assessment of the product to satisfy themselves that it is suitable for their requirements.

ALPIlignum Silver Rail /

ALPIlignum Silver Rail is a decorative veneer made of reconstituted wood with decorative aluminium pinstripes.

In line with the company's sustainable approach, ALPI veneer is made with wood from responsibly managed forests certified by the FSC® (FSC-C004666).



Standard dimensions /

Poplar based veneer	length 2500 mm width 300 mm - 600 mm (only for Wavy option)
Ayous based veneer	length 2500 mm width 300 mm - 600 mm (only for Wavy option)
Basswood based veneer	length 2500 mm width 300 mm - 600 mm (only for Wavy option)
Veneer nominal thickness	0.6 - 0.8 mm

ALPIlignum Silver Rail /

Formaldehyde emissions /

Measured according to the standard UNI EN 717-1:2004, the formaldehyde emission of ALPIlignum Silver Rail complies with EU REACH Regulation Eo5 under EU 2023/1464.

It is impossible to guarantee the absolute absence of formaldehyde, because traces of it are naturally present in wood.

Lightfastness /

ALPIlignum Silver Rail is an uncoated product whose lightfastness depends on the chemical composition of the final varnish and how it is applied. Upon request, ALPI supplies a type of ALPIlignum Silver Rail that can reach values above 4 in grey scale (UNI EN 15187:2024) if suitably varnished. Customers must be aware that exposure to light can make the veneer fade or change colour. ALPI suggests making precautionary tests based on the planned use in order to optimise performance.

Mechanical characteristics /

The mechanical characteristics of ALPIlignum Silver Rail depend on the chemical composition of the varnish used and the type of surface material the veneer is affixed to. ALPI suggests making precautionary tests based on the planned use in order to optimise performance.

Colour and grain /

Being a natural wood product, the colour of ALPIlignum Silver Rail may vary slightly from the reference colour. ALPI suggests verifying the colour and veining of the acquired veneer before use.

Storing /

Being prevalently made of wood, the humidity content of ALPIlignum Silver Rail varies in accordance with the humidity of the space where it is stored and processed. ALPI suggests maintaining relative humidity levels between 40% and 70%, with a reference ambient temperature of 20° Celsius.

Precautions /

Absolutely avoid contact, even temporary contact, with water and other liquids. Absolutely avoid condensation and dripping on the surface of the product. ALPIlignum Silver Rail must be stored flat, at least 20 centimetres from the ground, and protected from direct and indirect light.

ALPIlignum Silver Rail /

Veneering /

Gluing with urea adhesives

ALPIlignum Silver Rail can be glued with urea adhesive to all wood-based surfaces. Other types of surface must be tested and evaluated beforehand. The amount of glue per square metre depends on the material and thickness of the surface, on the structure and thickness of the veneer, and on press pressure. Generally, no more than 150 grams of glue per square metre is advised, combined with pressure between 1.5 and 5 bar. Veneering temperatures are between 85° and 120° Celsius. Glue may be mixed with organic or inorganic additives in order to modify the spread rate to reduce the effect of bleed-through, the occurrence of glue seeping through the pores of the wood and showing up on the face of the panel. Adding pigment to the glue in a colour similar to the veneer is advisable. ALPIlignum Silver Rail made of bass-wood must be glued with at least 120-140 grams of urea adhesive per square metre.

Glueing with vinyl adhesives

ALPIlignum Silver Rail can be glued with vinyl adhesive to all wood-based surfaces. Other types of surface must be tested and evaluated beforehand. Being thermoplastic, this type of adhesive must be applied in a precise quantity according to the veneer, the type of surface it is affixed to, and the type of press in order to avoid bleed-through that is difficult to eliminate by sanding. In general, between 80 and 100 grams of glue per square metre should be used, with pressure between 1.5 and 3.5 bar. Veneering temperatures are between 60° and 90° Celsius. Adding pigment to the glue in a colour similar to the veneer is advisable. ALPI suggests making tests before use.

Sanding /

After gluing it to the desired surface, ALPIlignum Silver Rail must be sanded with abrasive paper to eliminate imperfections and glue that has seeped through the pores. Sandpaper with grit grades 120–150–180 can be used singularly or in sequence, by hand or by electric sander. Grit grades 100 or 220/240 should only be used to obtain special effects.

Varnishing /

Like all other wood, ALPIlignum Silver Rail requires specific varnish to protect and preserve it from chemical and physical deterioration given by light and heat, and from mechanical damage such as scratches and dents.

ALPIlignum Silver Rail can be varnished using methods and types of product that are recommended for wood, but ALPI recommends avoiding the use of water-based varnish. ALPI suggests using products with high coating capacity, yellowing resistance, and good protection from ultraviolet rays.

ALPIlignum Silver Rail can be coated with two-component acrylic varnish, two-component polyurethane varnish, and UV-dried acrylic varnish – all in various degrees of shine. ALPI recommends following the instructions of the varnish manufacturer and conducting preliminary tests before proceeding.

For all additional clarifications, please contact the technical support office at ALPI. This data sheet replaces and annuls any older information. The information and recommendations contained in this data sheet are based on current knowledge at ALPI and could be modified in the future in accordance with new findings, evaluations or production systems.

Users should carry out their own assessment of the product to satisfy themselves that it is suitable for their requirements.

ALPIready /

ALPIready is a decorative surface in prefinished wood, ready for use, made of two layers of ALPIlignum joined by adhesive film. ALPIready is finished on the front side.

The product is durable, flexible and easy to use. ALPIready shortens the time and effort spent on panel fabrication and installation.

ALPI has chosen the most suitable finishes formulated to beautify the naturalness and colour of the wood.

ALPI also produces matching edge-banding for each pattern.

In line with the company's sustainable approach, ALPIready is made with wood from responsibly managed forests by the FSC® (FSC-C004666).

Application areas /

Furniture surfaces, interior-design surfaces, hotel interiors, surfaces in apartment buildings and residential complexes, boutiques, retail interiors, offices, public spaces, indoor facing and surfaces for yachts and cruise ships.

Finishes /

ALPIready is supplied with the most suitable finish.


Touch: Maintains the naturalness of the wood while being soft and pleasant to the touch.

Groove: Emphasises the grain and textural quality while being like raw wood to the touch.


Wax: A matt finish rendering the delicate appearance of wax-treated wood.

Oil: A finish that enlivens the colour of the wood while giving it the typical sheen of natural-oil treatments.

Product /



1. Finish
2. ALPIlignum wood veneer
3. Adhesive
4. ALPIlignum wood veneer



Available with matching edge-banding in wood.

ALPIready /

Size*	2500x1250/3050x1300 mm
Nominal Thickness	1.0 mm
Weight per m ²	0.7 kg
Variation in size (UNI EN 438-2, 17:2019)	1 %
Resistance to abrasion (UNI EN 438-2, 10:2019)	>20/25 Taber turns
Resistance to cold liquids (UNI EN 12720:2013)	A
Lightfastness (xenon arc lamp)** (UNI EN 438-2, 27:2019)	>4/5 Grey scale
Formaldehyde Emission Compliance with Annex 1 of the German Chemical Prohibition Ordinance (according to DIN EN 16516 and DIN EN 717-1)	✓
Certification	 The mark of responsible forestry FSC® C004666

*Some products come only in 1250 mm width

** The specific rating of lightfastness for each of the ALPIready products is available upon request.

ALPIready /

Helpful recommendations /

For correct counterbalance, we suggest using the same type of product on both sides of the panel, as advised by the EN 14323 standard. However, high-pressure laminate that has characteristics compatible with the outward-facing material can also be used. In any case, specific production tests must be carried out to evaluate the stability of the finished panel over time (three to seven days).

Preconditioning /

We advise conditioning the product for at least 48 hours in the same room as the panel to which it will be affixed. Optimal conditions are 20° Celsius with a relative humidity of 40%-65%.

Gluings with a steel-plate press /

The utmost care is needed in cleaning the plates of the press, in order to avoid dents or damage to the finished surface. A varnished surface that is damaged by particles pressed between the metal plate and the decorative surface are difficult to repair. The protective film must always be lying perfectly smooth on the surface of ALPIready, in order to avoid pressing folds into the surface.

Apply the veneer glue evenly, in the same quantity, on both sides of the panel. The quantity of glue must be dosed so that it does not leak out from the edges under pressure and damage the decorative surface.

Never allow the temperature to rise above 80° and 90° Celsius for durations from 2 to 3 minutes when using thermosetting glue. The application of ALPIready on surfaces with an elevated coefficient of thermal expansion (metal and other surfaces) could lead to warping and delamination due to sudden changes in temperature and humidity.

Gluings with contact adhesive /

Contact adhesives can be applied by hand or by machine. This must be done properly, in order to avoid blisters beneath the surface. Allow the solvent contained in the glue to evaporate completely.

Please note /

As with natural wood, ALPIready surfaces cannot guarantee an absolute colour match between different production batches. Slight differences of hue between different lots of product are not to be considered a defect.

As with natural wood, ALPIready reacts to sunlight and artificial light, both direct and indirect. A gradual change in the surface colour over time is a natural phenomenon.

Cleaning /

ALPIready surfaces are easy to clean with natural-fibre cloth moistened with water. Neutral, non-abrasive detergent may be used. Avoid the use of solvents such as acetone, nail polish remover or paint thinner.

Storing /

ALPIready must be stored horizontally, panels face to face, in rooms with a temperature between 10° and 30° Celsius, relative humidity between 40% and 60%, arranged on designated pallets, never resting directly on the floor.

As with all wood surfaces, for good preservation over time, ALPIready must be protected from the sun by means of opaque, possibly dark, covering. Absolutely avoid contact, even temporary contact, with water and other liquids. Absolutely avoid condensation and dripping on the surface of the product.

The panels must be handled by two people.

We recommend using the product within 12 months of delivery.

For all additional clarifications, please contact the technical office at ALPI. This data sheet replaces and annuls any older information.

The information and recommendations contained in this data sheet is based on current knowledge at ALPI and could be modified in the future in accordance with new findings, evaluations or production systems.

Users should carry out their own assessment of the product to satisfy themselves that it is suitable for their requirements.

Safety information /

Like all other ALPI products, ALPIready adheres to REACH legislation (the European Regulation on Registration, Evaluation, Authorisation and Restriction of Chemicals), which rules that substances of very high concern and substances subject to authorisation appear in concentrations of less than 0.1% by weight (REACH Annex XIV). ALPI products do not contain restricted substances (REACH Annex XVII), and they comply with the European Union Regulation 2019/1021 regarding persistent organic pollutants, which took effect on 20 June 2019. ALPI does not use metal-complex dyes.